

ASTM Standard Welded Steel Pipes - Schedule 40

ASTM A 53

Nominal Size	Outside Diameter		Outside Diameter				SCH No.	Wall Thickness		Calculated Weight				Test Pressure *			
			Maximum		Minimum					Plain Ends		Threads and Coupling		Grade A		Grade B	
	in	mm	in	mm	in	mm		in	mm	lb/ft	kg/m	lb/ft	kg/m	Psi	kPa	Psi	kPa
1/2	0.840	21.3	0.854	21.7	0.807	20.5	40	0.109	2.77	0.85	1.27	0.85	1.27	700	4830	700	4830
3/4	1.050	26.7	1.067	27.1	1.020	25.9	40	0.113	2.87	1.13	1.69	1.13	1.69	700	4830	700	4830
1	1.315	33.4	1.331	33.8	1.283	32.6	40	0.133	3.38	1.68	2.50	1.68	2.50	700	4830	700	4830
1 1/4	1.660	42.2	1.673	42.6	1.626	41.3	40	0.140	3.56	2.27	3.39	2.28	3.40	1200	8270	1300	8960
1 1/2	1.900	48.3	1.917	48.7	1.870	47.5	40	0.145	3.68	2.72	4.05	2.73	4.06	1200	8270	1300	8960
2	2.375	60.3	2.398	60.9	2.350	59.7	80	0.200	5.08	3.63	5.41	3.66	5.39	1800	12410	1900	13100
							40	0.154	3.91	3.65	5.44	3.68	5.46	2300	15860	2500	17240
2 1/2	2.875	73.0	2.902	73.7	2.846	72.3	80	0.218	5.54	5.02	7.48	5.07	7.55	2500	17240	2500	17240
							40	0.203	5.16	5.79	8.63	5.82	8.67	2500	17240	2500	17240
3	3.500	88.9	3.535	89.8	3.465	88.0	80	0.276	7.01	7.66	11.41	7.73	11.52	2500	17240	2500	17240
							40	0.216	5.49	7.58	11.29	7.62	11.35	2220	15310	2500	17240
3 1/2	4.000	101.6	4.039	102.6	3.961	100.6	80	0.300	7.62	10.25	15.27	10.33	15.39	2500	17240	2500	17240
							40	0.226	5.74	9.11	13.57	9.20	13.71	2030	14000	2370	16340
4	4.500	114.3	4.543	115.4	4.457	113.2	80	0.318	8.08	12.51	18.63	12.63	18.82	2800	19310	2800	19310
							40	0.237	6.02	10.79	16.07	10.89	16.23	1900	13100	2210	15240
5	5.563	141.3	5.618	142.7	5.508	139.9	80	0.337	8.56	14.98	22.32	15.17	22.60	2700	18620	2800	19310
							40	0.258	6.55	14.62	21.77	14.81	22.07	1670	11510	1950	13440
6	6.625	168.3	6.693	170.0	6.560	166.6	80	0.375	9.52	20.78	30.94	21.09	31.42	2430	16750	2800	19310
							40	0.280	7.11	18.97	28.26	19.18	28.58	1520	10480	1780	12270
8	8.625	219.1	8.712	221.3	8.539	216.9	80	0.432	10.97	28.57	42.56	28.89	43.05	2350	16200	2740	18890
							40	0.322	8.18	28.55	42.55	29.35	43.73	1340	9240	1570	10820
10	10.750	273.0	10.858	275.7	10.643	270.3	80	0.500	12.70	43.39	64.64	43.9	65.41	2090	14410	2430	16750
							40	0.365	9.27	40.48	60.29	41.85	63.36	1220	8410	1430	9860
12	12.750	323.8	12.878	327.0	12.623	320.6	80	0.594	15.09	64.43	95.97	-	-	1990	13720	2320	16000
							40	0.406	10.31	53.52	79.70	-	-	1150	7930	1340	9240
14	14.000	355.6	14.140	359.2	13.860	352.0	80	0.688	17.48	88.63	132.04	-	-	1940	13380	2270	15650
							40	0.438	11.13	63.50	94.55	-	-	1130	7790	1310	9030
16	16.000	406.4	16.160	410.5	15.840	402.3	40	0.500	12.70	82.85	123.30	-	-	1120	7720	1310	9030
18	18.000	457.2	18.180	461.8	17.820	452.6	40	0.562	14.27	104.67	155.87	-	-	1120	7720	1310	9030

Thickness Tolerances: ±12.5%

* Test Pressure For Plain End Pipes only.